

# Design


Hallite 87 bearing strip has the ability to support side loads and eliminate 'stick slip' between moving parts. The accurately dimensioned rectangular cross section is produced from a special combination of PTFE and Bronze materials. It has excellent heat resistance and strength to resist creep, making it suitable for bearings with reciprocating, oscillating or rotary movement, whether lubricated or not. Our standard range of cross section sizes are proportioned to be wrapped around a wide range of rod or piston diameters. Installation of the bearing is an easy task. Calculate and measure length L2 (see overleaf), cut the strip with a sharp blade and fit to the groove. If required we will be pleased to supply bearings to your sizes. Independent testing has established the typical properties which make the Hallite 87 worthwhile considering for many applications other than hydraulic or pneumatic cylinders. When using the compressive stress at yield in your calculation it is suggested a 4:1 factor of safety is applied.

The material is compatible with hydraulic mineral oil, lubricating oil, water based and synthetic fire resistant fluids and lubricating grease. Although the material is rated at 200°C, the recommended maximum temperature for bearing applications is 60°C.

Please send us details of your application for advice on this or any other problem where the Hallite 87 may solve your bearing problem.

# **Features**

- · Low friction
- · Infinite length range
- Easy installation
- · Extremely fllexible



### **Technical details**

#### **Operating Conditions**

Maximum Speed Temperature Range

# **Typical Physical Properties**

Specific Gravity
Compression Stress at Yield
Compression Stress at Yield
Coefficient of Thermal Conductivity
Coefficient of Thermal Expansion

Coefficient of Dynamic Friction

# **Bearing Strip Tolerances**

Surface Roughness
Dynamic Sealing Face  $\emptyset d_1 \emptyset D_1$ Static Housing Faces  $\emptyset D_2 L_1 \emptyset d_2$ 

# Housing Details & Tolerances

Rod

Piston

### Metric

5.0 m/sec -50°C +200°C

3.1 23°C 20 MN/m2 80°C 9 MN/m2 2.5 W/mK

Length & Thickness 6.5 x 10 -5 per °C

Dry Lubricated 0.25 0.05 L<sub>1</sub> S -0.1 -0.5 +0.03 -0.05

μmRa μmRt 0.4 4 max 3.2 max 16 max

-0 + 0.2

Inch

15.0 ft/sec -58°F +390°F

3.1 73°F 2900 p.s.i. 176°F 1300 p.s.i. 1.4Btu/hft°F

μinCLA	μinRMS
16	18
125 max	140 max

G min controls the minimum metal to metal clearance between the gland and rod or bore and piston.

G max controls the maximum extrusion gap seen by a seal associated with the bearing.

Typically, G min should be 0.7mm / 0.028" but can be reduced when required by the extrusion gap for the seal and the build up of tolerances.

The absolute minimum metal to metal clearance recommended is 0.1mm / 0.004"

For applications not using a seal G max – see

